



Kolzer

MILANO

ITALIA

TOP COAT - 610 post-metallization

PROTECTIVE VARNISH FOR VACUUM METALLIZATION FINITURES

CHARACTERISTICS: This product is recommended for countless applications, it is easily sprayed and has excellent dilatation. Once dried it has an hard film.

APPLICATION: Varnishing procedure is done by using spray guns or airless device manual or automatic.

COLOURING: For coloured items, add concentrate solution series S 11.../A in amount variable between 5% to 30% according to the desired colour intensity.

DRYNG: Varnish 610 is out of dust in 3 minutes and dries itself in the air in about 10 minutes. To speed up drying time, process on oven at 55° - 60°C for 5 minutes, may be used.

PACKAGING: Drums Kg. 19
 Drums Kg. 200

The above information and suggestion are to be considered indicative, they can be modified to better fit our products to materials and their surfaces. The above specifications are given without our responsibility because the use conditions are beyond our control.

April 2003